

Please replace the paragraph beginning at page 24, line 1, with the following rewritten paragraph:

[Table 3]

	Heating temp. (°C)	Peel strength (N/cm)
Ex. 3	100	4.1
	150	1.5
	180	5.2
	200	5.6
	250	5.3
	300	4.4
Comp. Ex. 3	no	1.2
Ex. 3a	no pressurizing 150°C	3.0